

32  
an anti-diffusion layer formed from an alloy containing said anti-diffusion metal and an adhesive metal, said anti-diffusion layer being formed between said bottom electrode and said ferroelectric thin film.

---

Please substitute the following claim 31 for the pending claim 31:

---

33  
31. The electromechanical transducer according to Claim 28, wherein said adhesive metal of said anti-diffusion layer is either titanium or chromium.

---

***In the Abstract:***

Please substitute the following abstract for the pending abstract:

---

34  
An electromechanical transducer is produced by the successive lamination of an adhesive layer, a bottom electrode, an anti-diffusion layer, a ferroelectric thin film, and a top electrode over an installation surface. The adhesive layer is formed from an alloy containing an anti-diffusion metal. The anti-diffusion layer is formed from an alloy containing the anti-diffusion metal and an adhesive metal.

---